

LEXAN™ XHRA13 FILM SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ XHRA13 is polycarbonate-copolymer film that is OSU compliant, low smoke and with good flame characteristics.

TYPICAL PROPERTY VALUES◆

PROPERTY	TEST METHOD	UNITS	TYPICAL VALUE
Physical			
Specific gravity	ASTM D792	g/cm ³	1.34
Water absorption, 50%RH, 23°C	ISO 62	g/cm ³	0.11
Water absorption, saturation, 23°C	ISO 62	%	0.28
Mechanical			
Tensile Strength @ Yield, 50mm/min	ASTM D 638	MPa	76
%Elongation @ Yield	ASTM D 638	%	9
Tensile Strength @ Break, 50mm/min	ASTM D 638	MPa	72
%Elongation @ Break	ASTM D 638	%	58
Tensile Modulus, 50mm/min	ASTM D 638	MPa	2900
Tear Strength – Propagation, Max Load – 2mil	SABIC Internal	N	0.17
Tear Strength – Initiation, Max Load – 2mil	SABIC Internal	N	5.24
Tear Strength – Propagation, Max Load – 3mil	SABIC Internal	N	0.29
Tear Strength – Initiation, Max Load – 3mil	SABIC Internal	N	9.12
Tear Strength – Propagation, Max Load – 5mil	SABIC Internal	N	0.62
Tear Strength – Initiation, Max Load – 5mil	SABIC Internal	N	17.60
Tear Strength – Propagation, Max Load – 7mil	SABIC Internal	N	1.06
Tear Strength – Initiation, Max Load – 7mil	SABIC Internal	N	23.57
Thermal			
Vicat Softening temperature, 50N, 50°C/h	ISO 306	°C	137
Vicat Softening temperature, 50N, 120°C/h	ISO 306	°C	139
Heat deflection temperature, 1.82MPa/3.2mm	ASTM D 638	°C	121
Coefficient of linear thermal expansion, -40 to 40°C	SABIC Internal	Um/(m·°C)	60
Flame Characteristics (2mil – 7mil film)			
Vertical burn, 60 seconds – Burning Time	FAR 25.853	Seconds	<1
Vertical burn, 60 seconds – Burning Length	FAR 25.853	Inches	<5
Vertical burn, 12 seconds – Burning Time	FAR 25.853	Seconds	<1
Vertical burn, 12 seconds – Burning Length	FAR 25.853	Inches	<5
Ohio state heat release	FAR 25.8539(d) App.F	Pass	
NBS smoke density, Ds max – Non Flaming	ASTM F812/E662	-	<10
NBS smoke density, Ds max – Flaming	ASTM F812/E662	-	0
Smoke toxicity – Flaming	BSS 7239	-	Pass
Smoke toxicity – Non Flaming	BBS 7239	-	Pass

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported Values are based on 4mil gauge thickness unless otherwise noted.

™ Trademark of SABIC.

CONTACT US:



ООО «Торгово-Строительная Компания Империя»

109382, Россия, г.Москва, ул.Нижние поля, 31
+7(495)646-81-65
info@tbc-empire.ru
www.tbc-empire.ru

LLC TBC Empire

109382, Russia, Moscow, Nizhniye polya,31
+7(495)646-81-65
info@tbc-empire.ru
www.tbc-empire.ru

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

[†] Any brands, products or services of other companies referenced in this document are the trademarks,

